



協承昌股份有限公司 JETCOAT CORPORATION

桃園縣 328 觀音工業區榮工南路 15 號／NO.15, Rong-Kong South Road, Guan-Inn Industrial District, Tau-Yuan, 328, Taiwan

電話／TEL：+886-3-4832953 傳真／FAX：+886-3-4832957

UV curable White ink series for compact disk-1

Product Code	Appearance	Viscosity @25°C cps	Total UV dosage* mJ/cm ²	Application Coating Machine	Features	Usages
WI-555D	White paste	22500±2500	140	Screen Printing	● High hiding power & adhesion ● Good whiteness & stability ● Basecoat for the printable ink.	Can be printed on CD、 CDR、DVD、DVDR
WI-486	White paste	25000±2500	140		● Low shrinkage ● High hiding power & adhesion ● Good whiteness & stability ● Basecoat for the printable ink.	
WI-331C	White paste	24000±2000	140		● High hiding power & adhesion ● Good whiteness & stability ● Good transfer for offset ink	
WI-325	White paste	22000±4000	140		● High hiding power & adhesion ● Good whiteness & stability ● Good transfer for offset ink	
P-225	White paste	23000±2000	140		● High hiding power & adhesion ● Good whiteness & stability ● Good transfer for offset ink	
NW-52	White paste	30000±2500	140		● High hiding power & adhesion ● Good whiteness & stability ● Non-Barium	

*The adjustment is necessary due to different conditions.



協承昌股份有限公司 JETCOAT CORPORATION

桃園縣 328 觀音工業區榮工南路 15 號／NO.15, Rong-Kong South Road, Guan-Inn Industrial District, Tau-Yuan, 328, Taiwan

電話／TEL：+886-3-4832953 傳真／FAX：+886-3-4832957

UV curable ink series for compact disk — 2

Product Code	Appearance	Viscosity @25°C cps	Total UV dosage [※] mJ/cm ²	Application Coating Machine	Features	Usages
JW-1A	Lemon yellow paste	17000±2000	120	Screen Printing	● Excellent gloss & leveling ● High adhesion 、 Low Shrinkage ● Adjustable multicolor	Can be printed on CD 、 CDR 、 DVD 、 DVDR
JW-2A	Yellow paste	22500±2500	120			
JW-3A	Orange Paste	25000±2500	120			
JW-4A	Red Orange Paste	24000±2000	120			
JW-5A	Red Paste	22000±4000	120			
JW-6A	Pink Paste	23500±1500	120			
JW-7A	Violet Paste	23000±3000	120			
JW-8A	Blue Paste	23000±2000	120			
JW-9A	Green Paste	30000±2500	120			
JW-11A	White paste	23000±2000	120			
JW-12A	Black paste	20500±3500	300			
DK-15	Black paste	15500±1500	300			

※The adjustment is necessary due to different conditions.



協承昌股份有限公司 JETCOAT CORPORATION

桃園縣 328 觀音工業區榮工南路 15 號／NO.15, Rong-Kong South Road, Guan-Inn Industrial District, Tau-Yuan, 328, Taiwan

電話／TEL：+886-3-4832953 傳真／FAX：+886-3-4832957

UV curable ink series for compact disk — 3

Product Code	Appearance	Viscosity @25℃ cps	Total UV dosage [※] mJ/cm ²	Application Coating Machine	Features	Usages
Y-531	Yellow Paste	30000±5000	120	Screen Printing	● Excellent gloss & leveling ● High adhesion 、Low Shrinkage ● Adjustable multicolor	Can be printed on PP, PE, PVC, PC, ABS, etc.
M-531	Magenta Paste	30000±5000	120			
C-531	Cyan Paste	30000±5000	120			
K-531	Black paste	30000±5000	120			

※The adjustment is necessary due to different conditions.



協承昌股份有限公司 JETCOAT CORPORATION

桃園縣 328 觀音工業區榮工南路 15 號／NO.15, Rong-Kong South Road, Guan-Inn Industrial District, Tau-Yuan, 328, Taiwan

電話／TEL：+886-3-4832953 傳真／FAX：+886-3-4832957

UV curable ink series for compact disk—4

Product Code	Appearance	Viscosity @25°C cps	Total UV dosage [*] mJ/cm ²	Application Coating Machine	Features	Usages
RP-168	Opaque Paste	12000±2000	140	Screen Printing	● Excellent Matt Silver effecting ● Good yellowing resistance	Can be printed on CD、CDR、DVD、DVDR
RP-451	Opaque Paste	12000±2000	140		● Excellent Matt Silver effecting ● Good yellowing resistance	Can be printed on CD、CDR、DVD、DVDR

UV curable ink series for printable compact disk—5

Product Code	Appearance	Viscosity @25°C cps	Total UV dosage [*] mJ/cm ²	Application Coating Machine	Features	Usages
PK-210A	Opaque Paste	11000±2000	140	Screen Printing	● Excellent matte leveling ● High adhesion, low shrinkage ● Excellent receptivity to printer ink	Can be printed on CD、CDR、DVD、DVDR
PK-210B	Opaque Paste	16500±1500	140		● Slightly rough surface ● High adhesion, low shrinkage ● Excellent receptivity to printer ink	
PG-7	Opaque Paste	11000±1000	140		● Glossy slightly rough surface ● High adhesion, low shrinkage ● Excellent receptivity to printer ink	
PG-9	Opaque Paste	7500±1000	140		● Glossy leveling surface ● High adhesion, low shrinkage ● Excellent receptivity to printer ink	

**JETCOAT**

協承昌股份有限公司 JETCOAT CORPORATION

桃園縣 328 觀音工業區榮工南路 15 號／NO.15, Rong-Kong South Road, Guan-Inn Industrial District, Tau-Yuan, 328, Taiwan

電話／TEL：+886-3-4832953 傳真／FAX：+886-3-4832957

UV curable coating series

Product Code	Appearance	Viscosity @25℃ cps	Total UV dosage [※] mJ/cm ²	Application Coating Machine	Features	Usages
PL-700	Clear, pale yellow liquid	60±3	140	Spin coating	● Low viscosity ● High purity ● Excellent protection and printability ● Low Shrinkage	CD protective lacquer
C-30	White paste/liquid	2000±500	140	Roller coating	● Excellent gloss and leveling ● High adhesion, low shrinkage ● The recoatability is good	Lacquer for PVC card or smart card.
PH-B-1	Clear, pale yellow liquid	6000±500	140	Spray coating	● Excellent gloss and leveling ● High adhesion ● High hardness.	UV spray hardcoat
CO-09	Clear, pale yellow liquid	450±50	140	Roller coating	● Excellent gloss and leveling ● High adhesion, ● Good recoatability to hot stamped ● Good flexibility .	UV varnish for PE tube.od

[※]The adjustment is necessary due to different conditions.



協承昌股份有限公司 JETCOAT CORPORATION

桃園縣 328 觀音工業區榮工南路 15 號／NO.15, Rong-Kong South Road, Guan-Inn Industrial District, Tau-Yuan, 328, Taiwan

電話／TEL：+886-3-4832953 傳真／FAX：+886-3-4832957

UV curable 12 colors screen printing ink for plastic — 1

Product Code	Appearance	Viscosity @25℃ cps	Total UV dosage  mJ/cm ²	Machine	Features	Usages
JE-100	Lemon yellow paste	5000±1000	120	Screen Printing	● Excellent gloss and leveling ● Good adhesion and flexibility ● Well reproductive, good hot stamping effect ● Multi-color blending ● Well performed on plastic substrates, PP、PE、PVC、ABS etc	Can be printed on PP, PE, PVC, PC, ABS, etc.
JE-200	Yellow paste	5000±1000	120			
JE-300	Orange Paste	5000±1000	120			
JE-400	Red Orange Paste	5000±1000	120			
JE-500	Red Paste	5000±1000	120			
JE-550	Deep Red Paste	5000±1000	120			
JE-600	Pink Paste	5000±1000	120			

 The adjustment is necessary due to different conditions.



協承昌股份有限公司 JETCOAT CORPORATION

桃園縣 328 觀音工業區榮工南路 15 號／NO.15, Rong-Kong South Road, Guan-Inn Industrial District, Tau-Yuan, 328, Taiwan

電話／TEL：+886-3-4832953 傳真／FAX：+886-3-4832957

UV curable 12colors screen printing ink for plastic — 2

Product Code	Appearance	Viscosity @25℃ cps	Total UV dosage** mJ/cm ²	Machine	Features	Usages
JE-700	Violet Paste	5000±1000	120	Screen Printing	● Excellent gloss and leveling ● Good adhesion and flexibility ● Well reproductive, good hot stamping effect ● Multi-color blending ● Well performed on plastic substrates, PP、PE、PVC、ABS etc	Can be printed on PP, PE, PVC, PC, ABS, etc.
JE-800	Blue Paste	5000±1000	120			
JE-900	Green Paste	5000±1000	120			
JE-1100	White paste	5000±1000	120			
JE-1200	Black paste	5000±1000	120			
JE-1800	White paste	5000±1000	120			
JE-1600	Black paste	5000±1000	120			



協承昌股份有限公司 JETCOAT CORPORATION

桃園縣 328 觀音工業區榮工南路 15 號／NO.15, Rong-Kong South Road, Guan-Inn Industrial District, Tau-Yuan, 328, Taiwan

電話／TEL：+886-3-4832953 傳真／FAX：+886-3-4832957

Label Over Print Products

products	Viscosity (25°C)	Appearance	Features	Curing Rate (80 watt/in Mercury lamp)	Applied machinery	Package
P-531P	80~100 cP	Clear, pale-yellow liq	● High gloss ● Excellent leveling ● Low yellowing	40 m/min	● Roller coater ● Flexographic printer	20kg/tin can 200KG/ Drum
P-531PN	80~100 cP	Clear, pale-yellow liq	● Good hot stamping effect ● High gloss ● Excellent leveling ● Low yellowing	40 m/min	● Roller coater ● Flexographic printer	20kg/tin can 200KG/ Drum
P-533J	320~380cP	Clear, pale-yellow liq	● High gloss ● Excellent leveling ● Low yellowing	40 m/min	● Roller coater ● Flexographic printer	20kg/tin can 200KG/ Drum
P-508J	250~310cP	Clear liq	● For outside food package ● High gloss ● Excellent leveling ● Low yellowing & low odor	40 m/min	● Roller coater ● Flexographic printer	20kg/tin can 200KG/ Drum
PA-1510	500~600cP	Clear, pale-yellow liq	● Low yellowing ● Simple operation ● Good adhesion for BOPP and PP film	40 m/min	● Roller coater ● Flexographic printer	20kg/platic pail 200KG/ Drum

※The adjustment is necessary due to different conditions.